

AMTECH

Advanced SMT Solder Products

SMT International, LLC
P.O. Box 989
Deep River, CT 06417
Toll free: 800.435.0317
Phone: 860.526.5300
Fax: 860.526.8243
www.amtechsolder.com

An ISO 9001 Certified Company

Product Data Sheet

NWS-4200-6 Water Soluble Solder Paste

Product Description

- Poly-dendrimer activator
- Long stencil life
- Wide process window
- Excellent wetting on OSP
- Increased wetting on oxidized components
- Compatible with enclosed printing heads

Alloys

AMTECH manufactures a low-oxide, spherical and uniformly sized powder. NWS-4200-6 is available in the following alloys: 63Sn/37Pb, 62Sn/36Pb/2Ag, 60Sn/Pb40, 43Sn/43Pb/14Bi, 42Sn/58Bi and Sn100.

Powder Distribution

Micron Size	Type	Pitch Requirements
75 - 45	Type-2	24mil & above
45 - 25	Type-3	16mil to 24 mil
38 - 20	Type-4	12mil to 16mil
25 - 15	Type-5	<12mil
15 - 5	Type-6	<8mil

Available Packaging

The following packaging options are available for stencil printing and dispensing applications: 250g and 500g jars; 250g and 700g cartridges; 750g ProFlow[®] cassettes; 35g and 100g syringes; 2,500g FreshMix[®] Kits.

Stencil Life

>8 hrs. @ 30–45% RH & 22–25°C
~4 hrs. @ 45–70% RH & 22–25°C

Viscosity

Printing applications: 600 to 800Kcps +/-10%
Dispensing applications: 350 to 425Kcps +/-10%
Tested according to IPC-TM-650

Tack Value

Typical tackiness: 34g force

Printing

The print definition of NWS-4200-6 is ideal for fine pitch applications. The stencil life of this water-soluble product virtually eliminates waste of solder paste. Consult the powder distribution chart to determine your mesh size requirements.

Printer Operation

The following are general guidelines for stencil printer optimization with NWS-4200-6. Some adjustments may be necessary based on your process requirements.
Print Speed: 25–100mm/sec
Squeegee Pressure: 0.2–0.7kg/inch of blade
Under Stencil Wipe: Once every 10–25 prints or as necessary

Stencil Cleaning

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using water at 60°C or 99% isopropyl alcohol (IPA). Post-reflow cleaning using water at 60°C with 50 PSI pressure.

Storage and Handling Procedures

Refrigerated storage at 42–47°F will prolong the solder paste shelf life to no less than 6 months. Syringes & cartridges should be stored vertically with the dispensing tip down. Solder paste should be allowed to reach ambient temperature naturally, prior to use (about 6-8 hours). NEVER FREEZE SOLDER PASTE.

(continued)

NWS-4200-6 Water Soluble Solder Paste


SMT International, LLC
 P.O. Box 989
 Deep River, CT 06417
 Toll free: 800.435.0317
 Phone: 860.526.5300
 Fax: 860.526.8243
www.amtechsolder.com

J-STD-004 (IPC-TM-650) Test Results


Test	Standard	Values	Results
Flux Designator	IPC-TM-650 2.3.35	NA	REH1

Recommended Profiles:

Profile-A was designed to serve as a starting point for process optimization using NWS-4200-6. A cool down rate of (-) 2–4°C/second is ideal for the formation of a fine grain structure without risking damage to thermally sensitive components.



A profile utilizing a soak of up to two minutes at 155°C may help to minimize voiding in BGA assemblies. This will allow more time for solvent components of the solder paste to outgas prior to reflow.



The information contained herein is based on technical data that we believe to be reliable and is intended for use by persons having technical skill, at their own risk. Users of our products should make their own tests to determine the suitability of each product for their particular process. AMTECH will assume no liability for results obtained or damages incurred through the application of the data presented.

AMTECH
 Advanced SMT Solder Products

Rev - 03/10